

Coating 134510

Ag + Multilayer

$|GDD-R_{s,p}(0-45^\circ, 550-1050\text{nm})| < 5\text{fs}^2$

$HR_u(0-45^\circ, 600-1000\text{nm}) > 98.5\%$

+ $HR_s(45^\circ, 540-1000\text{nm}) > 99\%$ + $HR_p(45^\circ, 580-1000\text{nm}) > 98\%$

fig. 1 calculated reflectivity 0-45°, unpolarized




fig. 2 calculated reflectivity 45°, s-/p-polarized




fig. 3 calculated GDD-R

