

HR(0°,1030-1090nm)>99.9% GDD-R(0°,1030-1090nm)= -250(±50)fs²

fig. 1 reflection HR-region 0°




fig. 2 calculated GDD(R,0°) with typically shift ±5nm of ZWL due to the production tolerance

